

Antique Heart Pine

- Species:** Southern Yellow / Heart Pine
- Source:** Hammonds Cold Storage Buildings, Chicago and other agricultural structures from different locations in North America.
- Grade:** Heritage Original™
- Knots:** 1 tight knot (1" or smaller) every 2' allowed. Larger knots in lower frequency allowed (for example: a 2" knot in a 4' length that is otherwise clear would be allowed). 2" maximum knot size allowed.
- Checks/Cracks:** Unlimited surface checking allowed. No splitting.
- Nail/Bolt Holes:** Occasional random nail holes visible. No bolt holes.
- Grain Pattern:** Tight grain, vertical, flat or mixed.
- Percentage Sapwood:** 20% (taken collectively)
- Color:** Deep rich copper brown.
- Weight:** 2.9 lb./Sq. Ft.
- Characteristics:** Appearance can be expected to vary from piece to piece, more so than with new lumber.
- Standard Dimensions:**
- a. Thickness: ¾"
 - b. Width: 3"-7"
 - c. Length: 18" – 10' with no more than 15% of total footage shorter than 4'.
- Textures Available:** Smooth, Wire Brushed, Circular Sawn, Skip Sawn, 3D, Hand Scraped, Hand Scraped Plus, Draw Knife Distressed.
- Additional Options:** Machine, Hand Scraped or Draw Knife Beveled Edges & Ends, Pegs.
- Installation:** **Texturewood®** flooring can be installed on and above grade level. It is not recommended that this flooring be installed below grade. Installation procedures may vary (i.e. reclaimed versus new floors, or strip versus plank flooring, etc.) We recommend consulting with a professional flooring installer, and following National Wood Flooring Association installation guidelines.
- Moisture Content:** Shipped at 6%-8.5% average. Moisture content may vary some based on the humidity level of the installation site. Therefore, we recommend flooring be acclimated on the job site in the same environment in which it will remain once installed, for a period of 1 to 3 weeks.
- Finishes:** Consult with your professional flooring installer.
- Stability:** Will expand and contract less than Red Oak.
- Waste:** We recommend approximately 15% cut and waste on traditional sub floor installations.
- Janka Rating:** 1225
- Samples:** Character marks such as knots, checks/cracks, sap, and natural color and grain patterns will vary with each plank. This is even more so in reclaimed wood due to weathering and use. Your floor will vary somewhat from samples and pictures shown.

Texturewood® flooring products are processed from solid kiln-dried stock lumber. These flooring materials should be acclimatized and installed in accordance with the National Wood Flooring Association recommendations. As each installation is unique, we urge you to contact a professional flooring installer for recommendations concerning jobsite evaluation and installation. Please contact your **Texturewood®** representative with any questions, or view our website for general tips and guidelines on installation.

PO Box 93 • 1446 E 1500 N
Terreton, ID 83450 US
(208) 663-4329 • Fax: (208) 663-4729
Email: sales@texturewood.com
www.texturewood.com